

دهان زيتي مطفي سيكو ديلوكس

وصف المنتج:

دهان زيتي مطفي أساسه مبني على راتنجات الألكيد وقد تم تصميمه خصيصا لإعطاء طبقة طلاء نهائية ناعمة ومستوية وغير لامعة وإعطاء تشطيبات مطفية وباهتة اللمعان للأسطح.

الاستخدامات:

يستخدم كطبقة نهائية للأسطح الداخلية والخارجية على الأسطح الإسمنتية، والحديدية والخرسانة وطبقات اللياسة وأعمال الخشب والجبس وتأسيسها.

المميزات العامة:

- تغطية جيدة ومعدل فرد كبير
- قوي التماسك مع الطبقات الأخرى
- مرونة ونعومة وانسيابية عالية
- مقاوم جيدة للعوامل الجوية

المواصفات الفنية:

الألوان:	ابيض أو حسب كرت الألوان مطفي
نوع التشطيب:	مطفي
نسبة المواد الصلبة:	58 – 67 %
الكثافة النوعية:	1.55 – 1.65 جم/لتر تقريبا
معدل التغطية:	10 – 14 م ² /لتر (عند 30 ميكرون لطبقة واحدة)
اللمعان:	30 (دقيقة) عند زاوية 60°
نقطة الوميض:	عند 40° م
توصية التخفيف:	5 – 10 % بالحجم
التخفيف:	باستخدام التتر البارد
أدوات التطبيق:	بالفرشاة أو الرولة أو مسدس الرش
وقت الجفاف:	يعتمد زمن الجفاف على درجة الحرارة والرطوبة حسب المناطق وحسب الفصول
جفاف السطحي:	3 ساعات تقريبا (عند 25°م)
جفاف الكامل:	24 ساعات تقريبا (عند 25°م)
أعادة تكرار الدهان:	8 ساعات تقريبا (عند 25°م)

تحضير السطح:

يجب أن يكون السطح سليما جافا وخاليا من الأوساخ والزيوت والشحوم والأتربة والغبار

طريقة الاستعمال:

أ – للأسطح الإسمنتية وطبقات اللياسة وأعمال الجبس والجدران:

1. طلاء طبقة واحدة من سيلرسيكو
2. معالجة السطح بمعجون سيكو للجدران
3. طلاء طبقة واحدة من أساس زيتي مطفي سيكو
4. يتم طلاء طبقتين من دهان زيتي لماع سوبر سيكو

ب – الأسطح الحديدية والخشبية:

1. يتم طلاء طبقة واحدة من أساس أوكسيد حديد زيتي سيكو
2. يتم طلاء طبقتين من دهان زيتي لماع سوبر سيكو

طريقة التخزين:

يحفظ المنتج لمدة 12 شهر في حالة جافة وغير مفتوحة بعيدا عن اشعة الشمس المباشرة وفي مكان جيد التهوية في درجة حرارة محيطية بين 25-35 درجة حرارية

التعبئة:

برميل حديد 14كجم – 17 كجم

Sico Matt Enamel Delux

DESCRIPTION: Non-Glossy matt interior, exterior enamel paint based on synthetic alkyd resins specially designed for a smooth, even, non-glossy finish to give matt and dull glossy surfaces.

MAIN USES: Used as a final coat for interior and exterior surfaces on cement, steel, concrete, plastering layers, woodworks and gypsum foundations.

FEATURES:

- Good coverage and high spreading rate
- Strong adhesion with other layers
- High flexibility, softness and fluidity
- Good resistance to weather factors

SPECIFICATIONS:

Color: White & colors as per Color Card

Finish: Matt

Solid contents: 58 – 67 %

Density: 1.55 – 1.65 gm/cm³

Coverage: 10 – 14 m²/Lit (at 30 micron DFT)

Gloss: 30 (min.) at 60 °

Flash Point: At 40°C

Dilution: With mineral spirit

Dilution Rate: 5 – 10 % by volume

Application Tools: Brush, Roller, or Spray Gun.

DRAYING TIME: Drying time depends on temp. & humidity depending on regions & seasons.

Touch dry: 3 Hours (At 25°C)

Full Cure: 24 Hours (At 25°C)

Recoat interval: 8 Hours (At 25°C)

SURFACE PREPARATION: Surfaces must be intact, dry, clean and free of dust, grease, dirt and grime

APPLICATION METHOD: **A- For cement surfaces, plaster layers, gypsum works and walls:**

1. Apply one coat of Sico sealer at 30 Microns
2. Treat the surface with two coats of Sico wall putty
3. Apply one coat of Sico matt oil primer
4. Apply two coats of Sico Semi-Gloss Enamel Super paint

B – For Metal & Wooden surfaces:

1. Apply one coat of Sico Metal Oxide primer
2. Apply two coats of Sico Semi-Gloss Enamel Super paint

STORAGE: Stored for 12 months in a dry, unopened condition, away from direct sunlight, well-ventilated place at an ambient temperature of 25-35 °C

PACKING: 14Kg - 17Kg Steel Drums