

دهان زياتي مطفي سيكو بريميوم

دهان زياتي مطفي أساسه مبني على راتنجات الألكيد وقد تم تصميمه خصيصاً لإعطاء طبقة طلاء نهائية ناعمة ومستوية وغير لامعة وإعطاء تشطيبات مطفية وباهة اللمعان للأسطح.

يستخدم كطبقة نهائية للأسطح الداخلية والخارجية على الأسطح الإسمنتية، والحديدية والخرسانة وطبقات اللياسة وأعمال الخشب والجبس وتأسيسها.

- تغطية جيدة ومعدل فرد كبير
- قوي التماسك مع الطبقات الأخرى
- مرنة ونعومة وانسيابية عالية
- مقاوم جيدة للعوامل الجوية

وصف المنتج:

الاستخدامات:

المميزات العامة:

المواصفات الفنية:

أبيض أو حسب كرت الألوان

مطفي

نسبة المواد الصلبة:

55 - 65%

الألوان:

نوع التشطيب:

1.53 - 1.63 جم/لتر تقريباً

الكتافة النوعية:

10 - 14 م²/لتر (عند 30 ميكرون لطبقة واحدة)

معدل التغطية:

30 (دقيقة) عند زاوية 60°

اللumen:

عند 40 م⁰

نقطة الوميض:

5 - 10 % بالحجم

توصية التخفيف:

باستخدام التتر البارد

التخفيف:

بالفرشاة او الرولة او مسدس الرش

أدوات التطبيق:

يعتمد زمن الجفاف على درجة الحرارة والرطوبة حسب المناطق وحسب الفصول

3 ساعات تقريباً (عند 25°C)

وقت الجفاف:

24 ساعات تقريباً (عند 25°C)

جفاف السطحي:

8 ساعات تقريباً (عند 25°C)

جفاف الكامل:

يجب أن يكون السطح سليماً جافاً وخالياً من الأوساخ والزيوت والشحوم والأتربة والغبار

تحضير السطح:

أ - للأسطح الإسمنتية وطبقات اللياسة وأعمال الجبس والجدران:

1. طلاء طبقة واحدة من سيلرسيكو
2. معالجة السطح بمجنون سيكو للجدران
3. طلاء طبقة واحدة من أساس زياتي مطفي سيكو
4. يتم طلاء طبقتين من دهان زياتي لامع سوبر سيكو

طريقة الاستعمال:

ب - للأسطح الحديدية والخشبية:

1. يتم طلاء طبقة واحدة من أساس أوكسيد حديد زياتي سيكو
2. يتم طلاء طبقتين من دهان زياتي لامع سوبر سيكو

طريقة التخزين:

يحفظ المنتج لمدة 12 شهر في حالة جافة وغير مفتوحة بعيداً عن أشعة الشمس المباشرة وفي مكان جيد التهوية في درجة حرارة محطة بين 25-35 درجة حرارية

برميل حديد 14 كجم - 17 كجم

التعبئة:

Sico Matt Enamel Premium

DESCRIPTION: Non-Glossy matt interior, exterior enamel paint based on synthetic alkyd resins specially designed for a smooth, even, non-glossy finish to give matt and dull glossy surfaces.

MAIN USES: Used as a final coat for interior and exterior surfaces on cement, steel, concrete, plastering layers, woodworks and gypsum foundations.

FEATURES:

- Good coverage and high spreading rate
- Strong adhesion with other layers
- High flexibility, softness and fluidity
- Good resistance to weather factors

SPECIFICATIONS:

Color: White & colors as per Color Card

Finish: Matt

Solid contents: 55 – 65 %

Density: 1.53 – 1.63 gm/cm³

Coverage: 10 – 14 m²/Lit (at 30 micron DFT)

Gloss: 30 (min.) at 60°

Flash Point: At 40°C

Dilution: With mineral spirit

Dilution Rate: 5 – 10 % by volume

Application Tools: Brush, Roller, or Spray Gun.

DRAYING TIME: Drying time depends on temp. & humidity depending on regions & seasons.

Touch dry: 3 Hours (At 25°C)

Full Cure: 24 Hours (At 25°C)

Recoat interval: 8 Hours (At 25°C)

SURFACE PREPARATION: Surfaces must be intact, dry, clean and free of dust, grease, dirt and grime

APPLICATION METHOD: **A- For cement surfaces, plaster layers, gypsum works and walls:**

1. Apply one coat of Sico sealer at 30 Microns
2. Treat the surface with two coats of Sico wall putty
3. Apply one coat of Sico matt oil primer
4. Apply two coats of Sico Semi-Gloss Enamel Super paint

B – For Metal & Wooden surfaces:

1. Apply one coat of Sico Metal Oxide primer
2. Apply two coats of Sico Semi-Gloss Enamel Super paint

STORAGE: Stored for 12 months in a dry, unopened condition, away from direct sunlight, well-ventilated place at an ambient temperature of 25-35 °C

PACKING: 14Kg - 17Kg Steel Drums